

Neoxid Suspensions and Precursors

For thermal spraying

| Name | Composition | Particle size |
|--------------|-------------------------|-------------------|
| Neoxid LQ CS | Cr_2O_3 | 0.4 μm |
| Neoxid LQ CL | Cr_2O_3 | 4.0 μm |
| Neoxid LQ A | Al_2O_3 | 1.2 μm |
| Neoxid LQ T | TiO_2 | 0.5 μm |
| Neoxid LQ Z | ZrO_2 | 0.7 μm |

Water or solvent as liquid media.

Other **Neoxid LQ suspensions** and mixtures are available.

Neoxid LQ precursors are made according to customer specifications.

